

## SELECTIVE CATALYTIC REDUCTION OF $\text{NO}_x$ OVER ACID-LEACHED MORDENITE CATALYSTS

Lars A.H. Andersson, Jan G.M. Brandin and C.U. Ingemar Odenbrand  
Department of Chemical Technology, Chemical Center, Lund University,  
Institute of Science and Technology, P.O. Box 124, S-221 00 Lund, (Sweden)

### ABSTRACT

Selective catalytic reductions of  $\text{NO}$ ,  $\text{NO}_2$  and mixtures of  $\text{NO}$  and  $\text{NO}_2$  over mordenite catalysts were studied. The activity of mordenite catalysts with different Si/Al ratios, obtained through acid leaching, decreased with the Al content of the mordenite. The change in activity with temperature and acid leaching together with the changes in contents of Fe and Al indicate that Lewis acids are active sites. These Lewis acids could be either Fe ions or Lewis acids formed on dehydroxylation of Brønsted acid sites. Activities of  $\text{NO}$  reduction on leached mordenites were correlated to the amount of adsorbed  $\text{NO}^+$  measured by IR. The activity in the reduction of  $\text{NO}_x$  revealed a maximal conversion at a  $\text{NO}_2/\text{NO}_x$  ratio of 0.5, indicating that the oxidation of  $\text{NO}$  or the decomposition of  $\text{NO}_2$  are the rate limiting step in the overall reduction.

### INTRODUCTION

Mordenite, a zeolite with a high Si/Al ratio, is well suited for SCR reduction of  $\text{NO}_x$  (1,2). It has a structure of parallel main channels, from which side pockets lead to oval small channels parallel to the main ones. The crystal structure resists hydro-thermal breakdown as well as acid environment. These are important properties of mordenite when used as a catalyst in flue gas treatment.

Four coordinated aluminium to oxygen in the zeolite lattice creates a negative charge in the structure. The charge is balanced by counter ions, located in channels and pockets of the structure.

Active centers of the catalyst are believed to be acidic centers (Brønsted- and/or Lewis acid sites) on the internal surface. The chemical character of the counter ions affects catalytic activity. H-substituted mordenite exchanged with transition metal ions such as Cu or Fe has shown good catalytic properties in SCR of  $\text{NO}_x$  with ammonia (2).

Investigation of the influence of  $\text{NO}_2/\text{NO}_x$  ratio on SCR with ammonia over  $\text{V}_2\text{O}_5/\text{TiO}_2\text{-SiO}_2$  has shown that the activity of  $\text{NO}_x$  reduction is favoured by coexisting  $\text{NO}$  and  $\text{NO}_2$  in the reaction system. Our results show, that the activity is strongly enhanced by a ratio of 0.5 especially in the temperature

systems with  $\text{NO}_2/\text{NO}_x$  ratios equal or greater than 0.5. According to Tuenter et al.  $\text{NO}_x$  reduction  $\text{NO}_2/\text{NO}_x$  ratio of 0.5 the activity was much higher compared to NO reduction over an industrial  $\text{V}_2\text{O}_5\text{-WO}_3\text{-TiO}_2$  catalyst.

Compared to a  $\text{V}_2\text{O}_5/\text{SiO}_2\text{-TiO}_2$  catalyst, mordenite shows one order of magnitude lower rate of reaction for NO reduction with ammonia (2,6). The difference in catalytic activity increases as the temperature is decreased from 600 to 470 K. In oxidation of NO H-mordenite has a higher catalytic activity than the compared catalyst (7,8).

It is possible, that the relatively poor catalytic effect of H-mordenite in NO reduction with ammonia is caused by competitive adsorption between water and one of the nitrogen oxides. Mizumoto et al. have shown these effects in the reduction of NO with ammonia over Cu(II)NaY (9).

The purpose of this study is to examine the influence of the aluminium content in H-mordenite, changed by acid leaching, on the catalytic reduction of NO,  $\text{NO}_2$  and  $\text{NO}_x$  with  $\text{NH}_3$ .

## EXPERIMENTAL

### Catalyst

The catalyst, a commercial H-mordenite "Zeolon 900 H" from Norton Ltd Zeolon 900 H, was leached by hydrochloric acid using two different methods. In the first method different extents of leaching were achieved by varying the acid concentration indexed SLx (x=molar conc). In the second 2M HCl was used to leach the catalyst for 1,2 or 3 periods of two hours each (indexed SLEx x=periods). These treatments gave seven catalysts with different Si/Al ratios.

TABLE 1

Catalyst characterization

Catalyst	Si (Weight % hydrous)	Al	Fe	d (nm)	SBET ( $\text{m}^2 \text{g}^{-1}$ )	Vpor ( $\text{cm}^3 \text{g}^{-1}$ )
Z900H	31.0	5.58	0.50	0.19489	472.1	0.207
SL1	32.2	5.06	0.28	0.19477	493.0	0.211
SL5	31.3	4.64	0.25	0.19466	-----	-----
SLconc	32.0	4.64	0.23	0.19471	-----	-----
SLE1	32.2	4.56	0.23	0.19469	-----	-----
SLE2	32.4	3.97	0.16	0.19447	505.7	0.223
SLE3	34.0	3.31	0.09	0.19415	528.7	0.239

The catalysts were characterized by XRF, AAS, X-ray diffraction analysis, BET N<sub>2</sub> adsorption and NH<sub>3</sub> adsorption. A thorough description of catalyst preparation and characterization methods can be found in (8). A summary of catalysts and characteristics is presented in Table 1.

#### Method and reaction conditions

The catalytic properties of the mordenite samples were tested in a stationary flow reactor. The procedure and the equipment have been described in a previous article (6). To avoid formation of NH<sub>4</sub>NO<sub>3</sub> and reaction of NH<sub>3</sub> in the NO<sub>x</sub>-converter of the analysing equipment the sample flows were scrubbed to remove NH<sub>3</sub> (7). The reactions, which were investigated, were reduction with ammonia of NO, NO<sub>2</sub> and mixtures of NO and NO<sub>2</sub> at different NO/NO<sub>x</sub> ratios. The conversions were measured as a function of temperature or NO/NO<sub>x</sub> ratio.


The flue gas was simulated by mixing the components, measured by flowmeters from gas cylinders with each component in N<sub>2</sub> at known concentration. NO and total NO<sub>x</sub> were analysed by a Beckman 955 chemiluminisence instrument before and after passage through the reactor. The catalyst samples (0.1-0.5 g with a particle size 0.71-0.85 mm) were subject to a gas load of 50-60 l (NTP) h<sup>-1</sup> at a total pressure of 200 kPa unless otherwise stated. The reaction conditions were varied according to Table 2.

The effects of external mass transfer and channelling were shown not to influence the reaction rates of reduction of NO over a V<sub>2</sub>O<sub>5</sub>/SiO<sub>2</sub>-TiO<sub>2</sub> catalyst (6). These experiments were performed at higher rates of reduction and smaller amounts of catalyst were used than in the case of reduction over mordenites. Consequently the influence of these effects is negligible in the reduction of NO<sub>x</sub> over mordenites.

TABLE 2  
Reaction conditions

	NO Red		NO <sub>2</sub> Red	NO <sub>x</sub> Red	
NO (ppm)	110	600	--	45	330
NO <sub>2</sub> (ppm)	--	--	100	50	270
NH <sub>3</sub> (ppm)	150	800	150	150	800
O <sub>2</sub> (%)	2	2	2	2	2
TEMP (K)	550-620	420-670	390-670	550-650	410-670
NO <sub>2</sub> /NO <sub>x</sub>	0	0	1	0-1	0.45
Catalyst (g)	0.1	0.5	0.1	0.1	0.5
S.V. (cm <sup>3</sup> g <sup>-1</sup> h <sup>-1</sup> )	500,000	100,000	500,000	500,000	100,000

A net production of  $\text{NO}_x$  was observed during preheating of  $\text{NO}_2 + \text{NH}_3 + \text{O}_2$  in  $\text{N}_2$  at temperatures exceeding 590 K. Tests with an empty reactor resulted in production of total  $\text{NO}_x$  amounting to 10% at 670 K. At the same time a change in  $\text{NO}_2/\text{NO}_x$  ratio from 1 to 0.8 was observed at the reactor inlet. It is believed, that partial reduction of  $\text{NO}_2$  by ammonia produces NO.



This reaction has previously been reported for reduction of  $\text{NO}_2$  in the same experimental setup (7). The change in  $\text{NO}_2/\text{NO}_x$  ratio at the reactor inlet influences the overall rate only at temperatures higher than 620 K.

The  $\text{NO}_2$  reduction experiments exhibited a hysteresis effect when they were performed at increasing or decreasing temperatures. Lower conversions were obtained, when data points were taken at increasing temperatures compared to points measured at decreasing temperatures. The hysteresis appeared below 550 K. The reason for this behaviour is believed to be the formation of unstable ammonium nitrate.

#### Mass transfer limitations

In order to evaluate the extent of intraparticle mass transfer, NO-reduction was performed over Z900H at constant  $W/F_{\text{NO}}$ , but at two concentrations of NO (570 ppm and 110 ppm). NO conversions at 650 K were 95 and 62% at the first and the second concentration levels respectively. If the reaction order is lower than 1, which is the order of mass transfer rate, a decreased reactant concentration will give an increased mass transfer influence on the overall reaction rate ( $r_{\text{obs}}$ ). An Arrhenius plot of the reaction rate at the two concentration levels with the rate constant ( $k_{\text{obs}}$ ) derived from the expression for a first order reaction in an integral reactor, gives an overall activation energy ( $E_{\text{obs}}$ ).

At mass transfer limited reaction conditions the effectiveness factor ( $\eta$ ) approaches the value of the inverse Thiele module (for  $\eta < 0.1$ ). Under these circumstances the intrinsic activation energy ( $E_{\text{intr}}$ ) can be derived, if  $\eta$  in the overall reaction rate expression is substituted by the inverse Thiele module (11).

The influence of the activation energies of diffusion ( $E_{\text{diff}}$ ), and of reaction ( $E_{\text{intr}}$ ) on  $E_{\text{obs}}$  is then given by:

$$E_{\text{intr}} = 2 \cdot E_{\text{obs}} - E_{\text{diff}}$$

At the lower concentration level (110 ppm  $\text{NO}_x$  and 150 ppm  $\text{NH}_3$ )  $\eta$  is assumed to be less than 0.1. If  $E_{\text{diff}}$  of  $\text{CH}_4$  in mordenite (12),  $7 \text{ kJ mole}^{-1}$ , is used as an approximation for  $E_{\text{diff}}$  for  $\text{NO}_x$ , the values for  $\text{NO}$ ,  $\text{NO}_2$  and  $\text{NO}_x$  reductions presented in Table 3 are obtained.

TABLE 3

Reduction	Rate ( $\text{mole g}^{-1}\text{h}^{-1}$ )	$E_{\text{obs}}$ ( $\text{kJ mole}^{-1}$ )	$E_{\text{intr}}$ ( $\text{kJ mole}^{-1}$ )	$E_{\text{obs}}$ ( $\text{kJ mole}^{-1}$ )	Temperature (K)
NO	$1.0 \cdot 10^{-7}$	$31 \pm 2$	$55 \pm 4$	$58 \pm 3$	500-600
$\text{NO}_2$	$3.6 \cdot 10^{-7}$	$41 \pm 7$	$75 \pm 14$	----	530-620
$\text{NO}_x$ (*)	$4.4 \cdot 10^{-7}$	$23 \pm 4$	$39 \pm 8$	$27 \pm 1$	500-600

\* $\text{NO}_2/\text{NO}_x = 0.45$

No result of  $\text{NO}_2$  reduction over 0.5 g Z900H is presented since 600 ppm concentration of  $\text{NO}_2$  caused formation of  $\text{NH}_4\text{NO}_3$  in the system. In reduction of NO the calculated  $E_{\text{intr}}$  is close to the value of  $E_{\text{obs}}$  from reaction over 0.5 g Z900H. This indicates that the influence of mass transfer is negligible in reductions of 600 ppm NO over 0.5 g Z900H and that the assumption of  $\eta < 0.1$  is valid. As the rates of reduction for  $\text{NO}_2$  and  $\text{NO}_x$  are faster than that of NO,  $\eta$  should be smaller. Therefore the calculated  $E_{\text{intr}}$  for reduction of  $\text{NO}_2$  and  $\text{NO}_x$  should be proper estimations of the true activation energies as well.

## RESULTS

### The reduction of NO

Results presented here were obtained at experimental conditions as stated above as level 1 (0.5 g catalyst, 600 vppm NO, 750 vppm  $\text{NH}_3$  and 2%  $\text{O}_2$  in  $\text{N}_2$ ).

Figure 1 shows the influence of temperature on the conversion of NO. The activity increases with temperature but decreases with increasing si/A1 ratio.

# Explore Litigation Insights

Docket Alarm provides insights to develop a more informed litigation strategy and the peace of mind of knowing you're on top of things.

## Real-Time Litigation Alerts



Keep your litigation team up-to-date with **real-time alerts** and advanced team management tools built for the enterprise, all while greatly reducing PACER spend.

Our comprehensive service means we can handle Federal, State, and Administrative courts across the country.

## Advanced Docket Research



With over 230 million records, Docket Alarm's cloud-native docket research platform finds what other services can't. Coverage includes Federal, State, plus PTAB, TTAB, ITC and NLRB decisions, all in one place.

Identify arguments that have been successful in the past with full text, pinpoint searching. Link to case law cited within any court document via Fastcase.

## Analytics At Your Fingertips



Learn what happened the last time a particular judge, opposing counsel or company faced cases similar to yours.

Advanced out-of-the-box PTAB and TTAB analytics are always at your fingertips.

## API

Docket Alarm offers a powerful API (application programming interface) to developers that want to integrate case filings into their apps.

## LAW FIRMS

Build custom dashboards for your attorneys and clients with live data direct from the court.

Automate many repetitive legal tasks like conflict checks, document management, and marketing.

## FINANCIAL INSTITUTIONS

Litigation and bankruptcy checks for companies and debtors.

## E-DISCOVERY AND LEGAL VENDORS

Sync your system to PACER to automate legal marketing.