

DRL - EXHIBIT 1022 DRL001 ihed by

ontrolled Release Society, Inc. Allwaukee Avenue 335 eld, IL 60015 USA

dition, 1997

ight@ 1997 by The Controlled Release Society, Inc.

hts reserved. No part of this publication may be reproduced, stored in a retrieval n, or transmitted in any form or by any means, electronic, mechanical, photocopying, ting, or otherwise, without the prior permission of the publisher.

1022-0178

d in the USA

ibstracts in this book are listed in the following:

oridge Scientific Abstracts nical Abstracts rpta Medica

Controlled Release Society assumes no responsibility ostracts not available at time of printing.

1997 Symposium and Workshop Scientific Program Committee

1997 Cochairs

Rad-Erik Folk, Astra Häusle AB, DSA Terno Okano, Tokyo Women's Medical College, Japan

1996 Chair

Singent H. J. Lee, University of Southern California, USA

1998 Cochairs

Kinam Park, Purdue University, USA Bussell O. Potts, Cygnus, USA

Committee

Maris Alonso, University de Santiago de Compostela, Spain

Besnia Huliquist Bengteson, Astra Draco AB, Sweden

Merton Device, University of Nottingham, England, UK

Buth Duncan, University of London, England, UK

Sear Engstrom, Lund Culversity, Sweden

Tom Ferguson, Eli Lille, USA

Sylvan Prank, Ohio State University, USA

Cersion Colomb, Hebrew University of Jerusalem, Israel

Bodeich Kopecek, University of Utah, USA

Parks Ropeckova, University of Utah, USA

Gaus-Michael Lehr. University of Sandand, Germany

Hans Lentieroas, Uppsala University, Sweden

Robert Lavy, University of Michigan, USA

Mary Marshall, Southwest Research Inst., DSA

Terry Mazer, Abbott Laboratories, USA

Colin Melia. University of Nottingham, England, UK

Derek O'Hagan, Chiron Corporation, USA

Judy Reese, Mousanto, USA

Vitichi Sugiyama, University of Tokyo, Japan

Victor Yang, Eniversity of Michigan, USA

311

G

R

1996-1997	Officers	of	the	Controlled	Release	Society,	Inc.	
-----------	----------	----	-----	------------	---------	----------	------	--

President	
Isuneji Nagui	
Hoshi University	
Rokyu, Japan	

Vice President Thomas Kissel

Philipps-University of Marburg Marburg, Carmany

Past President Bedřich Espeček University of Diah Salt Lake City, UT USA

Scientific Secretary

Robert Guray University of Geneva Geneva, Switzerland

President Elect Ronald A. Siegel University of California San Francisco, CA USA

Treasurer

Lisa Brannon-Peppas Biogel Technology, Inc. Indianapolis, IN

Administrative Staff of the Controlled Release Society, Inc.

Executive Director M. Judith Roseman CRS Administrative Headquarters 1020 Milwaukes Ave. Smite 333 Deerliedt, II. 60015 USA Phone: (847) 808-7071 Pax. (847) 808-7073 E-mail: crs@crsadudidq.org WWW: http://www.rsadudidq.org/

Financial Manager Robert C. Roestler College Station, TX USA

Board of Governors

European Manager Daphné L. Rouse School of Pharmacy University of Geneva 30. qual E. Anscrucet CR-1211 Geneva & Switzerland Pharmérax (4-41) 22 702 6339 C-matt Daphne Komp@pharm.anage.co.

Maria José Alonso Simon Renita Tielle Brandsted Susan Cady Jonathan Hadgraft Alifeuru Hashida

Scott Herbig

Jean-Paul Marte

isrno Okano Kathieen Buskos Haus Schreier Bubert Sparks Yuchi Sugiyamu Yladimir F. Torchilin Giyan Wikan

NY SESSION NAME	Paper #
adium Presentations3-224	201-414
Fuordos, June 17, 1997	261-261
Oral Drug Delivery	201-208
Transidermal and Iontophoretic Delivery	209-215
Defivery of Genes and Oligonucleotides	216-223
Techniques for Drug Delivery I	224-232
Pulmonal and Alveolar Drug Delivery	233-240
Drug Targeting 81-98 Minisymposium on Innovative Aspects of	241-249
Controlled Drug Release Sponsored by the	
CRS and Capsagei	250-256
Minisymposium on Delivery Strategies for Mucosal	
Immonization	257-261
Wednesday, func 18, 1997	391-340
New Materials & Principles and	22.00
Techniques for Drug Delivery II	301-308
Agricultural and Veterinary Applications of	F Sections
Controlled Release	309-316
Minisymposium on Targetable Drug Carriers	
for Drug Delivery151-160	317-321
New Materials & Principles and	222 222
Techniques for Drug Delivery III	322-330
Transmicosal Delivery	331-334
Minisymposium on Restenosis and	222.20
Local Drug Delivery Strategies	335-340
Thursday, June 19, 1997 Themed Session: Beyond Liposomes, Lipids as	401-414
Components in Drug Delivery Systems	401-405
Themed Session: Sustainable Agriculture—	405-403
Low Use Rate Agrachemicals	406-409
Minnsymposium on Drug Delivery to the Brain	410-414
125-1053	5001-6587
Pasters 1 225-646	5007-5299
Oral Drug Delivery	5001-5094
Finnsmucosal Delivery	5101-5117
New Materials & Principles and	- SALDE SALV
Techniques for Drug Delivery	5200-5299
Sinters 11	6002-6587
Delivery of Genes and Objectudes	6001-6022
Brausdermal and lontophoratic Delivery	6101-6120
Agreement and Verginary Applications of Controlled Release	6291-6211
Palmonal and Alveolar Dong Delivery	6301-6302
Drug Targeting T 749-880	6401-6466
New Materials & Principles and	A - 2 GPT
Techniques for Drug Delivery	6501-6587
key Words 1053-1956 https://linex 1057-1073	

Find authenticated

court documents

without watermarks

at docketalarm.com

were compared with experimental data in various cases. Figure 2 shows a comparison between experimental data and theoretical predictions for the case of ibuprofen, administered orally in humans (5). Total predicted absorption is 51%, near the experimental estimate. The good match of the data is obtained upon assuming an epithelial permeability of 7.8×10-6 cm/s.




Fig. 2 Comparison of experimental (symbol) and predicted (solid curve) serum concentration profiles for ibuprofen following oral administration to humans.

Figure 3 shows a comparison between experimental data and theoretical predictions for the case of GHRP-1. administered orally in humans (6). Theoretical absolute bioavailability is approximately 0.1%. The theoretical prediction is obtained upon assuming an epithelial permeability of 6×10-7 cm/s.




Fig. 3 Comparison of experimental (symbol) and predicted (solid curve) serum concentration profiles for GHRP-1 following oral administration to humans

The proposed theoretical model can be used to predict the absorbed systemic concentrations of therapeutics ranging from small liphophlic molecules to macromolecules.

REFERENCES

1. Kreydiyyeb, S.I., Bitar, K.M., Bikhazi, A.B. J. Pharm. Sci., 79, 494

2. Adson. A., Raub, T.J., Burton, P.S., Barsuhn, C.L., Hilgers, A.R., Audus, K.L., Ho, N.F. J. Pharm. Sci., 83. 1529 (1994).

3. Brenner, H., Edwards, D.A. Macrotransport Processes. Boston: Butterwitth-Heineman (1993).

4. Stoll, B., Batycky, R., Leipold, H., Milstein, S., Edwards, D. Submitted (1997).

5. Dressman, J.B., Bass, P., Ritschel. W.A., Friend, D.R., Rubinstein, A., Ziv, E. J. Pharm. Sci., 82, 857 (1993).

6. Bowers, C.Y. J. Ped. Endocrin. 6, 21

WATER SOLUBLE FILM FOR ORAL ADMINISTRATION

Jian-Hwa Guot and Horst Zerbe2

'Aqualon Division, Hercules Inc., 500 Hercules Rd., Wilmington, DE 19808-1599 *LTS Corp., 21 Henderson Dr., West Caldwell, NJ 97006

Introduction

Mucoadhesive dosage forms for application to the oral cavity which are designed to deliver therapeutic and/or cosmetic agents to the oral mucosa are known in the art. Sanvordeker and Leuno (1) described a mucoadhesive carrier allowing the controlled release of a therapeutic agent via the mucosal tissue comprising an anhydrous but hydratable polymer matrix and amorphous furned silica. An optional water-insoluble film can be added to provide a non-adhering surface. They also disclosed a trilaminate film suitable for prolonged delivery of an active ingredient in the oral cavity (2). In a similar way, Mizobuchi, et al. (3) disclosed a sheet-shaped adhesive preparation comprising an adhesive layer containing certain water-soluble and water-insoluble polymers and a water-insoluble carrier which can adhere to the oral mucosa. thereby releasing an active agent to the oral cavity. A number of attempts have been made to reduce the adverse feeling in the oral cavity caused by the rigidity and inflexibility of the support layer by introducing soft film supports (4-6). However, these devices still leave the patient with a considerable amount of residue from the water-insoluble support film thereby still causing a feeling of discomfort. The obvious solution to overcome this problem was to develop mucoadhesive films which completely disintegrate, or even completely dissolve in the saliva.

Invention

The present invention contemplates a fapidly dissolving film which can be adhered to the oral cavity thereby releasing a

pharmaceutically or cosmetically active agent, said film comprising water-soluble polymers, a combination of certain surfactants, one or more polyalcohols, and one or more pharmaceutically or cosmetically active ingredients. Optionally, the fermulation may contain colorants, sweetening agents, flavors, flavor enhancers, or other excipients commonly used to modify the taste of formulations intended for application to the oral cavity. The resulting film is characterized by an instant wettability which causes the film to soften immediately after application to the mucosal tissue thus preventing the patient from experiencing any prolonged adverse feeling in the mouth.

The film is manufactured using conventional coating and drying techniques. cut into pieces of a shape and size that meet the requirements of the specific application, and packaged into suitable containers.

Experimental

The mucoadhesive film of the present invention contains as essential components a water-soluble polymer or a combination of water-soluble polymers, a combination of surfactants, one or more polyalcohols, and a pharmaceutically or cosmetically active ingredient. The polymers used for the mucoadhesive film include polymers which are hydrophilic and water-dispersible. The combination of surfactants used for the mucoadhesive film is a mixture of nonionic surfactants. The amount of drug to be incorporated into the film depends on the kind of drug and is usually between 0.01 and 20% (w/w). Cosmetically active agents may include breath freshening compounds like menthol, other flavors or fregrances commonly used for oral hygiene, and/or

Priceed, 146"] . Symp. Leaf. (88) . Bloact . Mater. . (24) 1997) Controlled Release Contety, Inc.

ctives used for dental and/or oral eansing like quarternary ammonium ases. The mucoadhesive film according to e present invention can be prepared as llows: The active ingredient, surfactants, civalcohol, and possible other ingredients kcept the water-dispersible polymer are ssolved in a sufficient amount of a solvent hich is compatible to them. After a clear plution has been formed, the waterspersible polymer or mixture of waterspersible polymers is slowly added under irring until a clear and homogeneous olution has been formed. The solution is nated onto a suitable carrier material and ned to form a film. The carrier material just have a surface tension which allows re polymer solution to be spread evenly cross the intended coating width. The cating of the solution onto the carrier naterial can be performed using any onventional coating equipment.

The films with desired thickness were ut or punched out for the disintegration nd tensile strength tests. The tensile trength of the films was assessed using richsen (Model 474, A. M. Erichsen limbH, Germany) and was expressed as ne maximum force (N) (Figure 1). A 25-cm² Im was placed in the peri dish which was lled with deionized water, and the time for he film to totally disintegrate was recorded Figure 2). The decrease of integration time It formulations A to E was accompanied by he decrease of tensile force of the ormulations. This correlation indicated that he choice of the most optimal formulation ould be decided by using either the tensile trength or the disintegration test.

Conclusion

A composition containing therapeutic trents and/or breath freshening agents for use in the oral cavity is disclosed. The carrier comprises water-soluble polymers in combination with certain ingredients and provides a therapeutic and/or cosmetic effect. The film is coaled and dried utilizing existing coating technology and exhibits instant wettability followed by rapid

dissolution/disintegration upon administration in the oral cavity.

References

- (1) Sanvordeker, D.R. and Leung, S-H. S. US patent 5,047,244, 1991. (2) Sanvordeker, D.R. and Lenug, S-H. S.
- WO patent 91/06270, 1991.
 (3) Mizobuchi, T., Ohii, A., Sakoh, S, and
- Muguruma, Y. US Patent 4,876,092, 1989 (4) Kuroya, T. and Inoue, Y. European Patent 0-381-194-B1, 1990.
- (5) Blank, R.G., Mody, D.S., Kenny, R.J. and Aveson, M.C. US Patent 4,946,684, 1990
- (6) Inoue, T., Maeda, K. and Eguchi, Y. US Patent 5,206,010, 1993.




Figure 1: The tensile strength of polymer films.




Figure 2: The disintegration time of polymer films.

Proceed.Int'l.Symp.Control.Rel.Bioact.Mater.,24(1997) Controlled Rejease Society Inc

Water Soluble Polycations for Controlled Delivery Systems

Nandini Konar and Cherng-ju Kim

School of Pharmacy, Temple University, Philadelphia, PA 19140

Introduction

Drug delivery systems using ion exchange resins are one of the oldest processes [1]. Commercially available ion exchange resins are based on highly cross-linked poly(styrene/divinyl benzene) (sulfonated and quaternized) or cross-linked pely(methacrylic acid). Highly cross-linked gel type resins (negligible swelling) significantly sustain the release of a drug in the gel matrix, which yields \sqrt{t} release kinetics with a tailing.

Recently, swellable polyelectrolyte gel matrices have been extensively investigated as drug delivery systems. By varying the ionic pendant groups and the degree of cross-linking of the polymer chams, the degree of swelling of charged polyelectolytes may be tailored. Several investigators used cationic and anionic hydrophobic polymers consisting of tertiary amine and methacrylic acid or acrylic acid groups, respectively, for the release of drugs [2-4]. However, due to the pH dependent swelling characteristics of charged polymers containing tertiary amine or carboxylic acid pendant groups, it was not feasible for these ionic gels to be employed as oral delivery systems, because the pH condition changes as a dosage form travels along the gastro-intestinal (GI) tract. Nujoma and Kim [5] demonstrated a (pseudo) linear release of water soluble drugs from erodible, drug/resin complex, gel tablets using noncross-linked poly(sulfopropyl methacrylate potassium -co- methyl methacrylate) (PSPMK/MMA). Drug release from drug-PSPMK/ MMA, which has a drug loading of greater than 40 wt%, maintains zero-order release kinetics for a long period of time because the drug in the matrices is bound to the polymer side chain until the complex is dissociated by incoming counter ions. It was found that drug release was independent of the pH of the dissolution medium as long as the ionic strength was higher than 0.1 M which is commonly observed in the GI fluid [6]. In addition, tablets, which are a common extended release dosage form were successfully prepared from these drug/resin complexes.

In this study, we present the zero-order release kinetics of water soluble anionic drugs from erodible, drug/polycationic, matrices (tablets) using poly(trimethylaminoethyl methacrylate chloride -comethacrylate) (PTMAEMC/MMA):

Experimental Methods Synthesis of PTMAEMC/MMA and Preparation of Drug Resinate Tablets

PTMAEMC/MMA was prepared by the free-radical solution polymerization of PTMAEMC (40%) and MMA (60%) as reported earlier [7]. The polymer was dissolved in de-ionized water, and a drug solution was added to the polymer solution. The complexes precipitated in water were recovered and washed several times before being dried. The dried drug-resinates were crushed in a mortar and pestle to obtain powders. Tablets with drug-resinates and dextrose were fabricated in 9.0 mm diameter die and a flat surface punch with a Carver press.

Drug Release Kinetics Tests

The drug release kinetics from drug-resinate tablets were carried out in 0.01 M phosphate buffer containing different amounts of NaCl at 37°C by the USP basket method at 100 rpm, unless otherwise noted. Drug release was monitored on a HP8452A diode-array spectrophotometer at 250 nm and 290 nm for diclofenac Na and sulfathiazole Na as model drugs, respectively.

Results and Discussion

The effect of ionic strength on diclofenac Na release from drug-PTMAEMC/MMA complex tablets at pH 7 is shown in Figure 1. Tablets of 200mg weight were formulated with 20 % dextrose as a tablet binder. The buffer contained 0.01 M phosphate and NaCl ranging from 0.05 M to 0.2 M

Proceed [at'].Symp.Control.Rej.Ricact.Mater.,24(1997) Controlled Release Society, Ibc.

-229