



## ENCYCLOPEDIA OF TEXTILES

Judith Jerde



## **Encyclopedia of Textiles**

Copyright © 1992 by Judith Jerde

All rights reserved. No part of this book may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, recording, or by any information storage or retrieval systems, without permission in writing from the publisher. For information contact:

Facts On File, Inc. 460 Park Avenue South Facts On File Limited Collins Street

New York NY 10016

Oxford OX4 1XJ

USA

United Kingdom

## Library of Congress Cataloging-in-Publication Data

Jerde, Judith

Encyclopedia of textiles/Judith Jerde.

p. cm.

Includes bibliographical references and index.

ISBN 0-8160-2105-8

1. Textile fabrics—Dictionaries. I. Title.

TS1309.J47 1992

677'.003---dc20

91-20756

A British CIP catalogue record for this book is available from the British Library.

Facts On File books are available at special discounts when purchased in bulk quantities for businesses, associations, institutions or sales promotions. Please contact our Special Sales Department in New York at 212/683-2244 (dial 800/322-8755 except in NY, AK or HI) or in Oxford at 865/728399.


Text design by Donna Sinisgalli Jacket design by Ellie Nigretto Composition by Facts On File, Inc. Manufactured by Pacific Offset LTD. Printed in Hong Kong

10987654321


This hook is printed on acid-free paper



as keratin are composed of carbon, hydrogen, oxygen, nitrogen and sulfur, whereas the cellulosic fibers from which many textiles are made do not contain the latter two elements. When viewed through a microscope, wool fiber looks like a rod that gently tapers from root to tip, and is unmistakably characterized by scales, which are called epithelial scales. The scales are important, because they act as a protective covering for the fiber, which causes wool to be very resistant to wear. The scales are covered with two membranes: the epicuticle and the exocuticle, which greatly affect the manner in which dyes are received by wool. Until the advent of the scanning electron microscope, the presence of these two very thin membranes was unknown. Now, as a result of their discovery, much progress has been made in the



Wool cross section The Wool Bureau, Inc.



Crimp The Wool Bureau, Inc.

washing and dyeing procedures that are possible with

In contrast to cotton and other cellulosic fibers, wool is distinguished also by crimps in the fiber, sometimes as many as 30 per inch of length. These crimps create many tiny air pockets which impart to wool a resilient, spongy texture. This in turn gives wool a great degree of thermal insulation per weight of fabric. It also gives wool the ability to absorb a great deal of water before it becomes saturated. This is a source of additional warmth in a garment, since the wearer remains dry until the fabric reaches saturation.

Wool has been valued for centuries because of its unique characteristics that set it apart from other fibers. It resists dirt, it is flame resistant, and because of its absorptive qualities for water it resists the build-up of static electricity. Further, it resists both tearing and abrading, as well as snagging, pilling and crocking.

## History

There is historical evidence that wool is one of the first fibers to have been made into textiles. It is well known that wool existed in Babylonia as early as 4000 B.C. Indeed, it is interesting to note that the word Babylonia means Land of Wool. Sheep were raised and sold in ancient Mesopotamia to such a large extent that wool making could be described as a major industry. Also of note is the fact that the Sumerians sold wool throughout the known world in these early times. Around 2000 B.C., the Phoenicians not only traded wool but also introduced the art of weaving in the Mediterranean area.

In A.D. 45, the Romans are credited with having bred a new strain of sheep that would come to have great and