

**United States Patent** [19][11] **Patent Number:** **6,159,498****Tapolsky et al.**[45] **Date of Patent:** **Dec. 12, 2000**[54] **BIOERODABLE FILM FOR DELIVERY OF PHARMACEUTICAL COMPOUNDS OF MUCOSAL SURFACES**[75] Inventors: **Gilles H. Tapolsky; David W. Osborne**, both of The Woodlands, Tex.[73] Assignee: **Virotext Corporation**, The Woodlands, Tex.[21] Appl. No.: **09/144,827**[22] Filed: **Sep. 1, 1998****Related U.S. Application Data**

[63] Continuation of application No. 08/734,519, Oct. 18, 1996, Pat. No. 5,800,832.

[51] **Int. Cl.**<sup>7</sup> ..... **A61K 9/70**; A61K 47/38; A61M 37/00[52] **U.S. Cl.** ..... **424/449**; 424/448; 424/434[58] **Field of Search** ..... 424/449, 448, 424/434[56] **References Cited**

## U.S. PATENT DOCUMENTS

3,640,741	2/1972	Etes	106/170
3,996,934	12/1976	Zaffaroni	128/268
4,226,848	10/1980	Nagai et al.	424/19
4,250,163	2/1981	Nagai et al.	424/14
4,285,934	8/1981	Tinnell	424/148
4,286,592	9/1981	Chandrasekaran	128/260
4,292,299	9/1981	Suzuki	424/16
4,381,296	4/1983	Tinnell	424/148
4,517,173	5/1985	Kizawa et al.	424/16
4,518,721	5/1985	Dhabhar et al.	523/120
4,572,832	2/1986	Kigasawa et al.	424/19
4,668,232	5/1987	Cordes et al.	604/897
4,713,243	12/1987	Schiraldi et al.	424/151
4,715,369	12/1987	Susuki et al.	128/156
4,720,387	1/1988	Sakamoto et al.	.
4,740,365	4/1988	Yukimatsu et al.	424/435
4,765,983	8/1988	Takayanagi et al.	424/434
4,867,970	9/1989	Newsham et al.	424/81

4,889,720	12/1989	Konishi	424/448
4,894,232	1/1990	Reul et al.	424/439
4,900,554	2/1990	Yanagibashi et al.	424/448
4,906,463	3/1990	Cleary et al.	424/78
4,915,948	4/1990	Gallopo et al.	424/435
4,990,339	2/1991	Schull et al.	.
5,059,189	10/1991	Cilento et al.	604/307
5,064,654	11/1991	Berner et al.	424/448
5,081,157	1/1992	Pomerantz	514/781
5,081,158	1/1992	Pomerantz	514/781
5,116,621	5/1992	Oji et al.	424/445
5,137,729	8/1992	Kuroya et al.	424/435
5,192,802	3/1993	Rencher	514/535
5,196,202	3/1993	Konishi	424/448
5,298,258	3/1994	Akemi et al.	424/484
5,314,915	5/1994	Rencher	514/535
5,332,576	7/1994	Mantelle	424/443
5,462,749	10/1995	Rencher	424/484
5,466,465	11/1995	Royds et al.	424/449
5,505,956	4/1996	Kim et al.	424/448
5,780,047	7/1998	Kamiya et al.	.

## FOREIGN PATENT DOCUMENTS

0050480	4/1982	European Pat. Off.	.
0250187	12/1987	European Pat. Off.	.
0381194	8/1990	European Pat. Off.	.
0781546	7/1997	European Pat. Off.	.
2497098	7/1982	France	.
2582942	12/1986	France	.
56/100714	8/1981	Japan	.
0159604	10/1985	Japan	.
0262422	4/1988	Japan	.

*Primary Examiner*—Edward J. Webman*Attorney, Agent, or Firm*—Morrison & Foerster LLP[57] **ABSTRACT**

The present invention relates to water-soluble, bioerodable pharmaceutical delivery device for application to mucosal surfaces. The device comprises an adhesive layer and a non-adhesive backing layer, and the pharmaceutical may be provided in either or both layers. Upon application, the device adheres to the mucosal surface, providing drug delivery and protection to the treatment site.

**27 Claims, No Drawings**

**BIOERODABLE FILM FOR DELIVERY OF  
PHARMACEUTICAL COMPOUNDS OF  
MUCOSAL SURFACES**

This is a continuation of application Ser. No. 08/734,519  
filed Oct. 18, 1996, now U.S. Pat. No. 5,800,832.

**FIELD OF THE INVENTION**

The present invention relates generally to a bioerodable,  
water-soluble pharmaceutical carrier which adheres to  
mucosal surfaces for the localized delivery of pharmaceu-  
tical compounds and protection of the treatment site.

**BACKGROUND OF THE INVENTION**

The localized treatment of body tissues, diseases, and  
wounds requires that the particular pharmaceutical compo-  
nent be maintained at the site of treatment for an effective  
period of time. Given the tendency of natural bodily fluids  
to rapidly wash away topically applied pharmaceutical  
components, the topical treatment of wet mucosal tissues  
has been problematic. In the mouth, saliva, natural replace-  
ment of the mucosal tissue, and eating, drinking, and speak-  
ing movements are some of the problems that have limited  
the effectiveness and residence time of pharmaceutical car-  
riers.

Bioadhesive carriers are known in the art and include gels,  
pastes, tablets, and films. These products, however, may lack  
one or several of the preferred characteristic for an efficient  
and commercially acceptable pharmaceutical delivery  
device. Some characteristics which are preferred by users of  
bioadhesive carriers include water-erodability, ease of hand-  
ling and application to the treatment site, and ease of  
comfort with minimal foreign body sensation. Other pre-  
ferred characteristics for an effective and user-friendly prod-  
uct for the treatment of mucosal surfaces include the use of  
pharmaceutically approved components or materials; instan-  
taneous adhesion to mucosal surface upon application;  
increased residence time for the protection of the affected  
tissue or the delivery of the pharmaceutical component; and  
ease of removal of the delivery device from the affected  
tissue or natural dissolution of the delivery device at the  
delivery site.

Bioadhesive gels which are used for application to  
mucosal tissues and especially the oral cavity are known in  
the art. For example, U.S. Pat. No. 5,192,802 describes a  
bioadhesive teething gel made from a blend of sodium  
carboxymethyl cellulose and xanthan gum. The gel may  
also have potential use in the treatment of canker sores, fever  
blisters, and hemorrhoids. However, this type of pharmaceu-  
tical carrier has a very limited residence time, given that  
body fluids such as saliva quickly wash it away from the  
treatment site. Bioadhesive gels are also described in U.S.  
Pat. Nos. 5,314,915; 5,298,258; and 5,642,749. The gels  
described in those patents use an aqueous or oily medium  
and different types of bioadhesive and gelling agents.

Denture adhesive pastes are another type of bioadhesive  
product known in the art. However, these preparations are  
used primarily for their adhesive properties, to adhere den-  
tures to the gums, rather than for the protection of tissue or  
for the topical delivery of pharmaceuticals, although drugs  
such as local anesthetics may be used in the paste for the  
relief of sore gums. U.S. Pat. Nos. 4,894,232 and 4,518,721  
describe denture adhesive pastes. The '721 Patent describes  
a combination of sodium carboxymethyl cellulose and poly-  
ethylene oxide in polyethylene glycol.

Pastes have also been used as film protectants and as drug  
delivery systems. One such example having film forming

and adhesive properties is the product commercialized under  
the name Orabase®-B, which is a thick gel or paste for the  
relief of mouth sores. Ingredients include guar gum, sodium  
carboxymethyl cellulose, tragacanth gum, and pectin. Even  
though it does provide numbing to the area of application,  
the film forming behavior and bioadhesion do not last. Thus,  
this product has a limited residence time.

Bioadhesive tablets are described in U.S. Pat. No. 4,915,  
948. The water-soluble bioadhesive material used in this  
device is a xanthan gum or a pectin combined with an  
adhesion enhancing material such as a polyol. Although  
residence time is improved with the use of bioadhesive  
tablets, they are not user friendly, especially when used in  
the oral cavity, given the unpleasant feelings associated with  
their solidity, bulkiness, and slow dissolution time. Bioad-  
hesive tablets are also described in U.S. Pat. Nos. 4,226,848;  
4,292,299; and 4,250,163, and are single layer or bilayer  
devices having an average thickness of 0.2 to 2.5 mm. The  
bioadhesive tablets described in these patents utilize a  
non-adhesive component such as cellulose ether, a bioad-  
hesive component such as polyacrylic acid, sodium car-  
boxymethyl cellulose, or polyvinylpyrrolidone, and a binder  
for tableting purposes. The cellulose derivatives may or may  
not be water-soluble. The claimed cellulosic materials in the  
'299 Patent are methyl cellulose, hydroxypropyl cellulose,  
and hydroxypropylmethyl cellulose.

The use of bandages or bioadhesive laminated films,  
which are thinner and flexible and therefore have a  
decreased foreign body sensation, is described in U.S. Pat.  
Nos. 3,996,934 and 4,286,592. These products are used to  
deliver drugs through the skin or mucous. The laminated  
films usually include an adhesive layer, a reservoir layer, and  
a backing layer. Bioadhesive devices designed to release  
drug through the skin at a given rate and over a period of  
time are usually not water soluble, and are not dissolved or  
washed away by bodily fluids.

In addition to film systems for the delivery of drug  
through the skin, film delivery systems for use on mucosal  
surfaces are also known. These types of systems, which are  
water-insoluble and usually in the form of laminated,  
extruded or composite films, are described in U.S. Pat. Nos.  
4,517,173; 4,572,832; 4,713,243; 4,900,554; and 5,137,729.  
The '173 Patent describes and claims a membrane-adhering  
film consisting of at least three layers, including a pharma-  
ceutical layer, a poor water soluble layer, and an interme-  
diate layer. The pharmaceutical layer includes the drug and  
a cellulose derivative selected from hydroxypropyl  
cellulose, methyl cellulose, and hydroxypropyl methyl cel-  
lulose. The poor water soluble layer is made by the combi-  
nation of one or more cellulose derivatives with a poor water  
soluble fatty acid, and the intermediate layer is made of  
cellulose derivatives. The '832 Patent relates to a soft film  
for buccal delivery, made by the combined use of a water  
soluble protein, a polyol, and a polyhydric alcohol such as  
cellulose and polysaccharides, and also teaches the use of  
coloring or flavoring agents. The '243 Patent describes a  
single or multi-layered bioadhesive thin film made from  
40-95% water soluble hydroxypropyl cellulose, 5-60%  
water-insoluble ethylene oxide, 0-10% water-insoluble  
ethyl cellulose, propyl cellulose, polyethylene, or  
polypropylene, and a medicament. The films are three-  
layered laminates and include a bioadhesive layer, a reser-  
voir layer, and a non water-soluble outer protective layer.  
The '729 Patent teaches a soft adhesive film applicable to the  
oral mucosa containing a systemic drug and comprising a  
mixture of a vinyl acetate non water-soluble homopolymer,  
an acrylic acid polymer, and a cellulose derivative. Finally,

the '554 Patent describes a device for use in the oral cavity having an adhesive layer including a mixture of an acrylic acid polymer, a water-insoluble cellulose derivative, and a pharmaceutical preparation, and a water-insoluble or sparingly soluble backing layer. The adhesive layer contains the pharmaceutical, and upon application to the mucosal surface, delivers the drug. The '554 Patent also states that "it is impossible to achieve an adhesive device for application to body tissue without all three components, that is, acrylic acid polymer, water insoluble cellulose derivative and a water insoluble or sparingly soluble backing layer."

The previous examples of thin films to be applied in the oral cavity by adhesion onto the mucosal tissues all utilize polymers which are water-insoluble by nature or which are made water-insoluble by crosslinking, and claim a long residence time. They are satisfactory but do not provide a water soluble device with good adhesive properties. Therefore, following application for an expected period of time and the release of an amount of drug, the thin films made by water insoluble polymers must be peeled off of the site of application.

### SUMMARY OF THE INVENTION

The present invention relates to a novel water-soluble pharmaceutical carrier device for application to mucosal surfaces to provide protection of and delivery of pharmaceutical to the site of application, surrounding tissues, and other bodily fluids, having an effective residence time, with minimal discomfort and ease of use. In one embodiment, the device includes a mucoadhesive bilayer film disk which is water-soluble and bioerodable. In one embodiment, the pharmaceutical delivery device comprises a bilayer film disk having an adhesive layer and a backing layer, both water-soluble, having the pharmaceutical in either or both layers. The adhesive layer comprises a film forming polymer such as hydroxyethyl cellulose, hydroxypropyl cellulose, hydroxypropylmethyl cellulose, or hydroxyethyl methyl cellulose, alone or in combination, and a bioadhesive polymer such as polyacrylic acid, polyvinyl pyrrolidone, or sodium carboxymethyl cellulose, alone or in combination. The non-adhesive backing layer comprises hydroxyethyl cellulose, hydroxypropyl cellulose, hydroxyethylmethyl cellulose, hydroxypropylmethyl cellulose, polyvinyl alcohol, polyethylene glycol, polyethylene oxide, or ethylene oxide-propylene oxide co-polymers, alone or in combination. Methods for treating mucosal surfaces, surrounding tissues, and bodily fluids, by applying the bilayer film to the treatment site for drug delivery and protection of the site of application, are also provided.

### DETAILED DESCRIPTION OF THE INVENTION

In the present invention, a novel water soluble, bioerodable pharmaceutical device which adheres to mucosal surfaces is provided. The present invention finds particular use in the localized treatment of body tissues, diseases, or wounds which may have moist surfaces and which are susceptible to bodily fluids, such as the mouth, the vagina, or other types of mucosal surfaces. The device carries a pharmaceutical, and upon application and adherence to the mucosal surface, offers a layer of protection and delivers the pharmaceutical to the treatment site, the surrounding tissues, and other bodily fluids. The device provides an appropriate residence time for effective drug delivery at the treatment site, given the control of solubilization in aqueous solution or bodily fluids such as saliva, and the slow, natural disso-

lution of the film concomitant to the delivery. In one embodiment, the pharmaceutical delivery device comprises a bilayer film disk having an adhesive layer and a backing layer, both water-soluble, having the pharmaceutical in either or both layers.

Unlike bioadhesive gels and pastes known in the art, which have a very limited residence time, given the tendency of bodily fluids such as saliva to wash away the gel from the treatment site, the present invention offers an increased residence time because of its filmy consistency and components. A typical residence time for an aqueous gel or paste, such as Orajel®, Orabase®, or Kanka® is a few minutes. This short residence time is a consequence of a limited or poor adhesion. In a typical aqueous gel, the mucoadhesive components are either in solution, suspension, or swollen. Once applied to the mucosal surface, however, the water based gel does not instantaneously penetrate the lipophilic mucosal surface. The composition and water affinity of these gels results in a tendency to quickly mix with the saliva, rapidly pulling away the different components of the gel, and limiting the residence time. The same tendency is expected with pastes, the increase in viscosity only slightly delaying the timing. The present invention, by its solid form and its instantaneous adhesion to the mucosal surface, allows a lasting contact, a consequence of the entanglement of polymer chains and glycoproteins of the mucosal tissue which assures adhesion. Dissolution kinetics in the saliva and other aqueous media are influenced by the physical state of the device. While a gel or solution will readily mix with saliva and/or other bodily fluids, a solid form such as a crystalline, film, or precipitate of the same or similar composition is expected to dissolve more slowly.

Also, unlike the bioadhesive tablets which are known in the art, the pharmaceutical device of the present invention minimizes the discomfort associated with application of a foreign substance for a period of time sufficient to provide effective drug delivery to the treatment site. Although bioadhesive tablets do offer effective residence time, users of bioadhesive tablets experience unpleasant sensations due to their solidity, bulkiness, and slow dissolution time if erodable, especially when used in the oral cavity. Moreover, the typical thickness of bioadhesive tablets, which may or may not be water soluble, is a couple of millimeters, and because of their thickness, the preferred site of application is on the upper gingival area. This site is quite satisfactory for the systemic delivery of an active component, but may not be as satisfactory for local delivery. The device of the present invention offers the advantages of an effective residence time with minimal discomfort and ease of use, and is an appropriate vehicle for the local as well as systemic delivery of pharmaceutical, given its thinner, flexible form.

Finally, unlike the film systems known in the art which are used to deliver pharmaceutical through the skin or mucous, the device of the present invention is made of water-soluble components and is bioerodable. The use of water-soluble components allows the device to dissolve over a period of time, with natural bodily fluids slowly dissolving and eroding away the carrier, while the pharmaceutical remains at the application site. Unlike bandages and other non-water-soluble film systems, the user of the present invention does not have to remove the device following treatment. Nor does the user experience the sensation of the presence of a foreign object at the mucosal surface or within the body cavity, given that upon application, water absorption softens the device, and over time, the device slowly dissolves or erodes away.

The residence time of the device of the present invention depends on the dissolution rate of the water-soluble polymers used. The dissolution rate may be adjusted by mixing together chemically different polymers, such as hydroxyethyl cellulose and hydroxypropyl cellulose; by using different molecular weight grades of the same polymer, such as mixing low and medium molecular weight hydroxyethyl cellulose; by using crosslinking agents such as glyoxal with polymers such as hydroxyethyl cellulose for partial crosslinking; or by post-treatment irradiation or curing, which may alter the physical state of the film, including its crystallinity or phase transition, once obtained. These strategies might be employed alone or in combination in order to modify the dissolution kinetics of the device, without suppressing the water solubility characteristics of the component materials.

Upon application, the pharmaceutical delivery device adheres to the mucosal surface and holds in place. Water absorption softens the device quickly, diminishing and eliminating the foreign body sensation. As the device rests on the mucosal surface, delivery of the drug is provided. Residence times may vary, depending on the formulation and materials used, but may be modulated between a few minutes to several hours. Residence times which may be achieved with this invention include 30 minutes to about 3 or 4 hours. A preferred residence time for effective drug delivery is about 1 to 2 hours. In addition to providing drug delivery, once the device adheres to the mucosal surface, it also provides protection to the treatment site, acting as an erodible band aid.

In one embodiment, the present invention comprises a film disk having two layers—an adhesive layer and a non-adhesive backing layer—which are both water soluble and made of pharmacologically-approved materials. The pharmaceutical component may be included in either layer, although preferably, it is included in the adhesive layer, which is closest to the treatment site and which will have a slower dissolution time, given that the backing layer protects the interior, adhesive layer and will dissolve first.

The adhesive layer may comprise at least one film-forming water-soluble polymer, usually a cellulose derivative (the “film-forming polymer”) and at least one pharmacologically acceptable polymer known for its bioadhesive capabilities (the “bioadhesive polymer”). The film forming polymer may comprise hydroxyethyl cellulose, hydroxypropyl cellulose, hydroxypropylmethyl cellulose, hydroxyethylmethyl cellulose, or a combination thereof. Preferably, the film-forming polymer comprises hydroxyethyl cellulose. Preferably, in the case of hydroxyethyl cellulose, the average molecular weight (Mw estimated from intrinsic viscosity measurements) is in the range  $10^2$  to  $10^6$  and more preferably in the range  $10^3$  to  $10^5$ , while in the case of hydroxypropyl cellulose, the average molecular weight (Mw obtained from size exclusion chromatography measurements) is in the range  $50 \times 10^3$  to  $1.5 \times 10^6$ , and more preferably between  $80 \times 10^3$  to  $5 \times 10^5$ . The film-forming, polymer may be crosslinked or plasticized in order to alter its dissolution kinetics.

The bioadhesive polymer of the adhesive layer may comprise polyacrylic acid (PAA), which may or may not be partially crosslinked, sodium carboxymethyl cellulose (NaCMC), and polyvinylpyrrolidone (PVP), or combinations thereof. These bioadhesive polymers are preferred because they have good and instantaneous mucoadhesive properties in a dry, film state. In the case of sodium carboxymethyl cellulose, typical average molecular weights comprise 50,000 to 700,000, and preferably 60,000 to 500,

000, with a degree of substitution of 0.7. The substitution range varies between 0.5 and 1.5, and preferably between 0.6 and 0.9. The polyvinyl pyrrolidone can be characterized according to its average molecular weight and comprises between 5,000 and 150,000, preferably between 10,000 and 100,000. The simultaneous use of PAA with some grades of PVP may result in the precipitation of one or both components. This precipitation may not be ideal to obtain a homogenous layer and may slightly alter the overall adhesive properties of the device.

The adhesion properties of the present invention are the result of the entanglement of polymer chains and interactions with glycoproteins of the mucosal surface. The chemical nature of the bioadhesive polymers, including chain and side groups and crosslinking agents, generates interactions between the mucosal constituents and the polymer or polymers, such as physical entanglement, Van der Waals interactions, and hydrogen bonding. Given that the composition of mucosal tissues differs from one individual to another and changes naturally over time, the use of a combination of bioadhesive polymers or the use of a combination of different grades of the same polymer is preferred. The use of a combination of at least two bioadhesive polymers maximizes the adhesion capabilities of the device, although use of a single bioadhesive polymer is effective as well.

The ratio of the bioadhesive polymer to the film-forming polymer in the adhesive layer may vary, depending on the type of pharmaceutical and the amount of pharmaceutical to be used. However, the content of combined components in the adhesive layer is between 5 and 95% by weight, preferably between 10 and 80% by weight. In terms of weight percent of the different bioadhesive polymers PAA, NaCMC, and PVP, some examples are provided below. Preferred combinations include PAA and NaCMC, NaCMC and PVP, or PAA and PVP, and also include the use of different grades of the same polymer.

The non adhesive backing layer may comprise a water-soluble, film-forming pharmaceutically acceptable polymer such as hydroxyethyl cellulose, hydroxypropyl cellulose, hydroxypropylmethyl cellulose, hydroxyethylmethyl cellulose, polyvinylalcohol, polyethylene glycol, polyethylene oxide, ethylene oxide-propylene oxide co-polymers, or a combination thereof. The backing, layer component may or may not be crosslinked. In one embodiment, the preferred backing layer component comprises hydroxyethyl cellulose or hydroxypropyl cellulose, and more preferably comprises hydroxyethyl cellulose. Preferably, in the case of hydroxyethyl cellulose, the average molecular weight (Mw estimated from intrinsic viscosity measurements) is in the range  $10^2$  to  $10^6$ , and more preferably in the range  $10^3$  to  $10^5$ , while in the case of hydroxypropyl cellulose, the average molecular weight (Mw obtained from size exclusion chromatography measurements) is in the range of  $50 \times 10^3$  to  $1.5 \times 10^6$  and more preferably from  $80 \times 10^3$  to  $5 \times 10^5$ .

Combinations of different polymers or similar polymers with definite molecular weight characteristics may be used in order to achieve preferred film forming capabilities, mechanical properties, and kinetics of dissolution. Some combinations for use in the invention are provided in the examples below and may include  $\frac{3}{4}$  of hydroxyethyl cellulose and  $\frac{1}{4}$  of hydroxypropyl cellulose;  $\frac{2}{5}$  of low molecular weight hydroxyethyl cellulose and  $\frac{3}{5}$  of medium molecular weight hydroxyethyl cellulose; and  $\frac{1}{2}$  of low molecular weight hydroxyethyl cellulose and  $\frac{1}{2}$  of high molecular weight hydroxyethyl cellulose. In order to modify the water dissolution kinetics of the backing layer without resulting in

a non-water soluble material, partial and limited crosslinking may be used. Crosslinking agents known in the art are appropriate for use in the invention and may include glyoxal, propylene glycol, glycerol, dihydroxy-polyethylene glycol of different sizes, and butylene glycol. The amount of crosslinking agent used may vary, depending on the particular polymers and crosslinking agent, but should not exceed 5% molar equivalent of the polymeric material, and preferably comprises 0 to 3% molar equivalent of the polymeric material. Dissolution characteristics may be adjusted to modify the residence time and the release profile of a drug when included in the backing layer.

The pharmaceutical component of the present invention may comprise a single pharmaceutical or a combination of pharmaceuticals, which may be incorporated in the adhesive layer, the backing layer, or both. Pharmaceuticals which may be used, either alone or in combination, include anti-inflammatory analgesic agents, steroidal anti-inflammatory agents, antihistamines, local anesthetics, bactericides and disinfectants, vasoconstrictors, hemostatics, chemotherapeutic drugs, antibiotics, keratolytics, cauterizing agents, and antiviral drugs.

Examples of anti-inflammatory analgesic agents include acetaminophen, methyl salicylate, monoglycol salicylate, aspirin, mefenamic acid, flufenamic acid, indomethacin, diclofenac, alclofenac, diclofenac sodium, ibuprofen, ketoprofen, naproxen, pranoprofen, fenoprofen, sulindac, fenclofenac, clidanac, flurbiprofen, fentiazac, bufexarnac, piroxicam, phenylbutazone, oxyphenbutazone, clofezone, pentazocine, mepirizole, tiaramide hydrochloride, etc. Examples of steroidal anti-inflammatory agents include hydrocortisone, prednisolone, dexamethasone, triamcinolone acetonide, fluocinolone acetonide, hydrocortisone acetate, prednisolone acetate, methylprednisolone, dexamethasone acetate, betamethasone, betamethasone valerate, flumetasone, fluorometholone, beclomethasone dipropionate, etc.

Examples of antihistamines include diphenhydramine hydrochloride, diphenhydramine salicylate, diphenhydramine, chlorpheniramine hydrochloride, chlorpheniramine maleate isothipendyl hydrochloride, tripelenamine hydrochloride, promethazine hydrochloride, methidiazine hydrochloride, etc. Examples of local anesthetics include dibucaine hydrochloride, dibucaine, lidocaine hydrochloride, lidocaine, benzocaine, p-buthylaminobenzoic acid 2-(di-ethylamino) ethyl ester hydrochloride, procaine hydrochloride, tetracaine, tetracaine hydrochloride, chloroprocaine hydrochloride, oxyprocaine hydrochloride, mepivacaine, cocaine hydrochloride, piperocaine hydrochloride, dyclonine, dyclonine hydrochloride, etc.

Examples of bactericides and disinfectants include thimerosal, phenol, thymol, benzalkonium chloride, benzethonium chloride, chlorhexidine, povidone iodine, cetylpyridinium chloride, eugenol, trimethylammonium bromide, etc. Examples of vasoconstrictors include naphazoline nitrate, tetrahydrozoline hydrochloride, oxymetazoline hydrochloride, phenylephrine hydrochloride, tramazoline hydrochloride, etc. Examples of hemostatics include thrombin, phytonadione, protamine sulfate, aminocaproic acid, tranexamic acid, carbazochrome, carboxochrome sodium sulfanate, rutin, hesperidin, etc.

Examples of chemotherapeutic drugs include sulfamine, sulfathiazole, sulfadiazine, homosulfamine, sulfisoxazole, sulfisomidine, sulfamethizole, nitrofurazone, etc. Examples of antibiotics include penicillin, meticillin, oxacillin,

cefalotin, cefalordin, erythromycin, lincomycin, tetracycline, chlortetracycline, oxytetracycline, metacycline, chloramphenicol, kanamycin, streptomycin, gentamicin, bacitracin, cycloserine, etc.

Examples of keratolytics include salicylic acid, podophylum resin, podolifox, and cantharidin. Examples of cauterizing agents include the chloroacetic acids and silver nitrate. Examples of antiviral drugs include protease inhibitors, thymidine kinase inhibitors, sugar or glycoprotein synthesis inhibitors, structural protein synthesis inhibitors, attachment and adsorption inhibitors, and nucleoside analogues such as acyclovir, penciclovir, valacyclovir, and ganciclovir.

The amount of active pharmaceutical (s) to be used depends on the desired treatment strength, although preferably, the pharmaceutical component comprises 0.001 to 30% by weight of the device, and more preferably between 0.005 and 20% by weight.

Plasticizers, flavoring and coloring agents, and preservatives may also be included in the pharmaceutical delivery device of the present invention in the adhesive layer, the backing layer, or both. Preferably, these components comprise no more than 1% of the final weight of the device, but the amount may vary depending on the drug or other components.

The thickness of the device may vary, depending on the thickness of each of the layers. Preferably, the bilayer thickness ranges from 0.05 mm to 1 mm, and more preferably from 0.1 to 0.5 mm. The thickness of each layer may vary from 10 to 90% of the overall thickness of the bilayer device, and preferably varies from 30 to 60%. Thus, the preferred thickness of each layer may vary from 0.01 mm to 0.9 mm, and more preferably from 0.03 to 0.6 mm.

The pharmaceutical delivery device of the present invention may be prepared by numerous methods known in the art. In one embodiment, the components are dissolved in the appropriate solvent or combination of solvents to prepare a solution. Solvents for use in the present invention may comprise water, methanol, ethanol, or low alkyl alcohols such as isopropyl alcohol, acetone, methyl ethyl ketone, heptane, or dichloroethane, alone or combination. The final solvent content or residual solvent content in the film may be the result of either or both layers. The solvent may also be used as a plasticizer or dissolution-rate-modifying agent.

Each solution is then coated onto a substrate. Eventually, one of the components might be in suspension. Each solution is casted and processed into a thin film by techniques known in the art, such as by film dipping, film coating, film casting, spin coating, or spray drying using the appropriate substrate. The thin film is then dried. The drying step can be accomplished in any type of oven. However) the solvent residual depends on the drying procedure. The film layers may be filmed independently and then laminated together or may be filmed one on the top of the other.

The film obtained after the two layers have been laminated together or coated on top of each other may be cut into any type of shape, for application to the mucosal tissue. Some shapes include disks, ellipses, squares, rectangles, and parallelograms.

Methods for treating mucosal surfaces, surrounding tissues, and bodily fluids for localized and systemic drug delivery are also provided. In one embodiment, the method comprises applying an adherent film of the invention to the treatment site in order to provide protection to the treatment site and drug delivery. The adherent film may comprise any of the bilayer devices provided in herein. In a preferred embodiment, the method comprises application of a bilayer

# Explore Litigation Insights

Docket Alarm provides insights to develop a more informed litigation strategy and the peace of mind of knowing you're on top of things.

## Real-Time Litigation Alerts



Keep your litigation team up-to-date with **real-time alerts** and advanced team management tools built for the enterprise, all while greatly reducing PACER spend.

Our comprehensive service means we can handle Federal, State, and Administrative courts across the country.

## Advanced Docket Research



With over 230 million records, Docket Alarm's cloud-native docket research platform finds what other services can't. Coverage includes Federal, State, plus PTAB, TTAB, ITC and NLRB decisions, all in one place.

Identify arguments that have been successful in the past with full text, pinpoint searching. Link to case law cited within any court document via Fastcase.

## Analytics At Your Fingertips



Learn what happened the last time a particular judge, opposing counsel or company faced cases similar to yours.

Advanced out-of-the-box PTAB and TTAB analytics are always at your fingertips.

## API

Docket Alarm offers a powerful API (application programming interface) to developers that want to integrate case filings into their apps.

## LAW FIRMS

Build custom dashboards for your attorneys and clients with live data direct from the court.

Automate many repetitive legal tasks like conflict checks, document management, and marketing.

## FINANCIAL INSTITUTIONS

Litigation and bankruptcy checks for companies and debtors.

## E-DISCOVERY AND LEGAL VENDORS

Sync your system to PACER to automate legal marketing.