

CONCISE ENCYCLOPEDIA OF PLASTICS

edited by
Donald V. Rosato
M.G. Rosato
Dominick V. Rosato

Kluwer Academic Publishers

Dynacraft BSC, Inc.

Exhibit 1011

Dynacraft v. Mattel

IPR2018-00042

DOCKET
A L A R M

Find authenticated court documents without watermarks at docketalarm.com

Distributors for North, Central, and South America:

Kluwer Academic Publishers
101 Philip Drive
Assinippi Park
Norwell, Massachusetts, 02061 USA
Telephone (781) 871-6600
Fax (781) 871-6528
E-mail <kluwer@wkap.com>

Distributors for all other countries:

Kluwer Academic Publishers Group
Distribution Centre
Post Office Box 322
3300 AH Dordrecht, THE NETHERLANDS
Telephone 31 78 6392 392
Fax 31 78 6546 474
E-mail <orderdept@wkap.nl>



Electronic Services <<http://www.wkap.nl>>

Library of Congress Cataloging-in-Publication Data

Rosato, Donald V.

Concise encyclopedia of plastics / Donald V. Rosato, Marlene G.

Rosato, Dominick V. Rosato

p. cm.

Includes bibliographical references and index.

ISBN 0-7923-8496-2 (acid-free paper)

1. Plastics Encyclopedias. I. Rosato, M. G. II. Rosato,

Dominick V. III. Title.

TP1110.R66 1999

668.4'03—dc21

Copyright © 2000 by Kluwer Academic Publishers.

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, mechanical, photocopying, recording, or otherwise, without the prior written permission of the publisher, Kluwer Academic Publishers, 101 Philip Drive, Assinippi Park, Norwell, Massachusetts 02061.

Printed on acid-free paper.

Printed in the United States of America.

evenly, and the ability to endure sustained production without constant maintenance. Using low-cost material to meet high performance requirements will compromise mold integrity. For example, for more than 90% of the molds, the cost of the cavity and core materials is less than 5% of the total mold cost. See **cost, product; mold cost. mold cavity, debossed.** Depressed or indented lettering or designs in the cavity that produce debossed impressions on the molded part. See **decorating, fill-and-wipe.**

mold-cavity deposit A plastic build-up on a cavity's surface that is due to plate out of the plastic and usually is attributed to the use of certain additives.

mold-cavity draft On most molded parts, features must be cut into the surface of the mold perpendicular to the molding parting line. To properly release the part from the tool, parts almost always include a taper. The amount of mold draft required will depend on factors such as type of plastic being processed, processing conditions, and surface finish. For example, a highly polished surface will require less than an unpolished mold. Any surface texture will increase the draft at least 1° per side for every 0.001 in. (0.003 cm) depth of texture. Special mold-cavity surface action can be used. Elastomeric material has a rubbery condition and may not require the draft for ejection. Also called *draft in the direction of the mold*. See **mold-parting line; mold release agent.**

mold cavity, duplicate-plate A removable plate that retains cavities and is used where a two-plate operation is necessary for loading inserts.

mold cavity, etched A surface that is treated with an acid, leaving relief to form the desired design texture on the molded part. See **chemical etching; photoetching tool; surface treatment; texturizing.**

mold-cavity ejector Various mechanical means that are used to eject or remove the molded part from the cavity.

mold cavity, female The indented half of a mold that is designed to receive the male half. See **mold cavity, male.**

mold-cavity fill and pack See **injection molding, boost cut-off or two-stage control.**

mold-cavity filling See **mold-filling monitoring.**

mold-cavity finish, SPI/SPE Mold Standard See **surface finish.**

mold cavity, frozen-layer Plastic melt begins to "freeze" (solidify) as it fills an injection-molding mold cavity. The frozen layer can easily vary in thickness as the mold fills, producing different frictional shear forces. As a result, flow (filling) and solidification (thermoplastic cooling) should be evaluated together. See **freeze-off.**

mold-cavity grit blasting Blowing steel grit or sand onto the cavity wall to produce a rough surface. This surface treatment may be required to permit air to leave the

mold cavities by forcing a hob into a relatively s blank. Hobbing is a technique where a master n hardened steel is used to sink the shape of the cav a heated mild steel, such as beryllium copper. Th larger than the finished plastic molded part beca hobbing, the metal shrinks during cooling. See **erosive cutting and sinking.**

mold-cavity honing Using a fine-grained wh or equivalent to obtain precise accuracy of the finish.

mold cavity, injection The two halves of th have a flat parting line. When the two halves me half is literally making contact by one flat surface another flat surface. Pressure on the injected mel cavity is through the plasticator's pressure-ram ac the melt. See **clamping; mold cavity, compr molding pressure required.**

mold-cavity land The length in the different g; figurations that influence melt flow.

mold cavity, male The extended half of a m is designed to match the female half. Also called See **mold-cavity filling.**

mold-cavity melt-flow analysis A compre understanding of the mold filling process. Detaile mation is generated concerning the influence of filling conditions on the distribution flow patter vectors, shear stresses, frozen skin, temperatures, ai sures. From these data, conclusions regarding e tolerances as well as part quality strength, appeara weld line can be drawn. The likelihood of warpi face, blemishes, and strength reductions due to hig stress can be anticipated. On this analysis, the best a practical mold-filling conditions can be selected. Se **model; injection-molding melt flow; injection ing process-control parameter; melt-flow ai processing fundamental; temperature transiti**

mold-cavity melt fountain flow The melt that enters the cavity (injection molding) by fo fountain (balloon) stretching effect. The stretchin front-oriented outer surface covers the inside wal cavity. Melt that follows basically fills in the founta: The result is a nonuniform orientation in the cross-of-the molded part; however, parts can still meet part mance requirements. The degree of ballooning or formation is controllable so that specific desired pr can be obtained. See **injection-molding melt flc**
mold-cavity packing See **cushion; mold monitoring; packing factor.**

mold-cavity plating See **mold-cavity coatir**
mold-cavity pressure The cavity pressure can corded via a transducer such as one being locatec cavity near the gate. It can plot a profile that record: ent information such as filling, packing, and holdir