

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



PREMIUM EXTRUSION AND RIGID PACKAGING RESINS

Marlex® EHM 6007

HIGH DENSITY POLYETHYLENE

This high molecular weight ethylene homopolymer is tailored for lightweight blow molded containers that require:

- Excellent stiffness
- Low taste and low aroma transfer

Typical blow molded applications for EHM 6007 include:

- Dairy bottles
- Liquid food packaging

This resin meets these specifications:

- ASTM D4976 - PE 244
- FDA 21 CFR 177.1520(c) 2.2, use conditions B through H per 21 CFR 176.170(c)
- Listed in the Drug Master File

NOMINAL PHYSICAL PROPERTIES ⁽¹⁾	English	SI	Method
Density	---	0.964 g/cm ³	ASTM D1505
Melt Index, 190/2.16	---	0.70 g/10 min	ASTM D1238
Tensile Strength at Yield, 2 in/min, Type IV bar	4,400 psi	30 MPa	ASTM D638
Elongation at Break, 2 in/min, Type IV bar	>300%	>300%	ASTM D638
Flexural Modulus, Tangent - 16:1 span:depth, 0.5 in/min	240,000 psi	1,650 MPa	ASTM D790
ESCR, Condition A (100% Igepal), F ₅₀	15 h	15 h	ASTM D1693
Brittleness Temperature, Type A, Type I specimen	<-103°F	<-75°C	ASTM D746

1. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1.

Dynacraft BSC, Inc.
Exhibit 1013
Dynacraft v. Mattel
IPR2018-00042

MSDS #240370

Revision Date January, 2005

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further information contained

DOCKET
ALARM

Find authenticated court documents without watermarks at docketalarm.com.